

Bradford Gold™ Ceiling

Product Description



Bradford Gold ceiling insulation is a resilient and compressible insulation manufactured from the controlled felting of glasswool bonded with a thermosetting resin.

- Designed to reduce energy costs by keeping heat out in summer and heat in during winter
- 42% of heat loss in a house is lost through the ceiling
- Designed to reduce unwanted noise entering your home to give you a quieter, more relaxing environment

Application

- To be used for ceiling and under floor applications, not designed for wall application
- Pieces are supplied in 430mm widths for joists spaced at 450mm centres and can be readily cut in half for joists at 600mm centres
- Has a guaranteed R-Value and complies to AS/NZS 4859.1
- Carries a lifetime guarantee

Standard Sizes and Packaging

R Value	Size (mm)	Area / Bale	Coverage / Bale	Items / Bale	NRC	Multi-Pac Sizes
R1.8	1160 x 430 x 95	12m ²	13.5m ²	24	-	6 bales
R2.2	1160 x 430 x 115	13m ²	14.6m ²	26	-	5 bales
R2.7	1160 x 430 x 145	10m ²	11.2m ²	20	1.00	5 bales
R3.2	1160 x 430 x 165	8m ²	9m ²	16	1.05	6 bales
R3.6	1160 x 430 x 185	8m ²	9m ²	16	-	5 bales
R4.0	1160 x 430 x 215	6m ²	6.7m ²	12	-	6 bales
R5.0	1160 x 430 x 210	4m ²	4.5m ²	8	-	4 bales
R6.0	1160 x 430 x 260	3m ²	3.4m ²	6	-	5 bales

Maximum Service Temperature

Bradford Gold is intended for use at temperatures normally prevailing in building structures. Maximum service temperature: 350°C.

Flow Resistivity

0.5 x 10⁴ mks Rayls/m.

Bradford Gold™ Ceiling

Acoustic Performance

Sound Transmission Loss (dB)

Frequency (Hz)	125	250	500	1000	2000	4000	5000	NRC
R2.7 Ceiling	0.66	0.96	1.09	0.98	1.02	1.05	1.02	1.00
R3.2 Ceiling	0.94	1.03	1.09	1.01	1.08	1.02	1.08	1.05

Fire Resistance Properties

Tested in accordance with AS/NZS 1530 Part 3-1999, Bradford Gold has the following fire indices:

- ✧ Ignitability 0
- ✧ Heat Evolved 0
- ✧ Spread of Flame 0
- ✧ Smoke Developed 0

Corrosion Resistance

Bradford Gold is faintly alkaline and incapable of corroding steel. To maintain this condition, protection must be provided against contamination from external sources. When tested in accordance with BS 3958 Part 5-1969, Bradford Gold pH is 7.5-8.0.

Moisture Resistance

Exposure to an atmosphere of 50°C and 95% relative humidity for four days, results in moisture absorption of less than 0.2% by volume. If the insulation becomes wet, full thermal efficiency will be restored on drying out.

Breathe Easy

Bradford Gold is great for the environment. Not only is it manufactured using up to 70% recycled glass but saving energy also reduces greenhouse gas emissions which is great news for the planet.

All Bradford products are manufactured to stringent standards and meet the requirements of AS/NZS 4859.1 and carry BRANZ certification so they can be used in any home to meet the New Zealand building regulations.

And they come with a lifetime guarantee backed by CSR - one of Australasia's oldest and largest building materials companies.

 **Bradford™**
for smarter environments

CSR Bradford Insulation

Monier Place, Penrose, Auckland

Telephone (09) 5799 059

Facsimile (09) 5711 017

Website www.bradfordinsulation.co.nz

CSR Bradford Insulation is a business division of CSR Building Products New Zealand Limited

The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Bradford insulation. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification. The purchaser should independently determine the suitability of the product for the intended use and application.


BRANZ Appraised
Appraisal No.301 [2005]


CSR